

Laboratorio prove, Centro di Ricerca, Sperimentazione, Consulenza e Controllo qualità

Main Laboratory Sassuolo S.r.l. - Via F.lli Setti, 7 - 42019 Scandiano - Reggio Emilia (Italy) Cod.Fisc. e P.IVA 03164360368
Tel: 0522 982603 Fax: 0522 852834 E-mail: info@mainlaboratorysassuolo.it Web: www.mainlaboratorysassuolo.it

TEST REPORT n. 3628/2021/I

**DETERMINATION OF DYNAMIC COEFFICIENT OF FRICTION (DCOF) OF HARD SURFACE FLOORING MATERIALS
ANSI A326.3:2019**

Date of report:	06/22/2021
Customer:	Terratinta Group S.r.l. Via Monte Bianco, 55 41042 Fiorano Modenese (MO)
Requested on:	06/07/2021
Our ref.number:	30644
Execution place of tests:	Scandiano (RE)
Description of the sample:	"Ceramic tiles marked:JOINT GRAPHITE MATT" 7x28 cm
Sampling:	carried out by the customer
Receipt date of samples:	06/08/2021
Execution date of tests:	start: 06/21/2021 end: 06/21/2021
Test specification:	ANSI A326.3:2019 Determination of dynamic coefficient of friction (DCOF) of hard surface flooring materials.
Warnings:	<i>This test report can not be reproduced in part, without our written consent. The reported results relate only to the samples tested. The information included in quotation marks was provided by the customer.</i>

Laboratorio prove, Centro di Ricerca, Sperimentazione, Consulenza e Controllo qualità

Main Laboratory Sassuolo S.r.l. - Via F.lli Setti, 7 - 42019 Scandiano - Reggio Emilia (Italy) Cod.Fisc. e P.IVA 03164360368
Tel: 0522 982603 Fax: 0522 852834 E-mail: info@mainlaboratorysassuolo.it Web: www.mainlaboratorysassuolo.it

TEST REPORT n. 3628/2021/I**DETERMINATION OF DYNAMIC COEFFICIENT OF FRICTION (DCOF) OF HARD SURFACE FLOORING MATERIALS
ANSI A326.3:2019**

Scope: this standard describe the test method for measuring dynamic coefficient of friction (DCOF) of hard surface flooring materials. This method can be used in the laboratory or in the field.

Procedure: the test is performed using Regan Scientific Instruments' BOT 3000E instrument in wet conditions using 0,05 % Sodium-Lauryl Sulfate (SLS) in water. The SBR rubber sensor is used as a sliding element with standard characteristics as described in point 4.2. The sensor is controlled using a standard tile before and after the test. Three (3) tile samples are tested in four (4) directions. field

Number of samples tested: 3

BOT 3000E calibration date: 01/08/2021

Type of surface: Flat

Cleaning chemical: FILA® PS87

Length of the path: 10 inch (maximum possible path - as per paragraph 9.6.1.1)

Conditions of the test: Wet surface

Type of sensor: SBR rubber

DCOF (wet) of sensor validation surface

Before the test: 0,36

After the test: 0,36

Test results

Sample	Direction 1	Direction 2	Direction 3	Direction 4	DCOF Average
1	0,75	* n.e.	0,77	* n.e.	0,76
2	0,62	* n.e.	0,64	* n.e.	0,63
3	0,58	* n.e.	0,65	* n.e.	0,62

* not executed



The Director
Giulia Gaido

End of document